

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



Rec'd PCT/PTO 07 APR 2005



(43) International Publication Date  
6 May 2004 (06.05.2004)

PCT

(10) International Publication Number  
WO 2004/038054 A1

(51) International Patent Classification<sup>7</sup>: C22C 33/02

(21) International Application Number:  
PCT/SE2003/001595

(22) International Filing Date: 15 October 2003 (15.10.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
0203135-9 23 October 2002 (23.10.2002) SE

(71) Applicant (for all designated States except US): HÖ-  
GANÄS AB [SE/SE]; S-263 83 Höganäs (SE).

(72) Inventor; and

(75) Inventor/Applicant (for US only): YU, Yang [SE/SE];  
Betesvägen 80, S-263 54 Höganäs (SE).

(74) Agent: AWAPATENT AB; Box 5117, 200 71 Malmö  
(SE).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,  
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,  
CZ (utility model), CZ, DE (utility model), DE, DK (utility

model), DK, DM, DZ, EC, EE (utility model), EE, ES, FI  
(utility model), FI, GB, GD, GE, GH, GM, HR, HU, ID,  
IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT,  
LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO,  
NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK,  
SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC,  
VN, YU, ZA, ZM, ZW.


(84) Designated States (regional): ARIPO patent (GH, GM,  
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,  
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,  
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

#### Declarations under Rule 4.17:

— as to applicant's entitlement to apply for and be granted  
a patent (Rule 4.17(ii)) for the following designations AE,  
AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA,  
CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES,  
FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,  
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,

[Continued on next page]

(54) Title: A METHOD OF CONTROLLING THE DIMENSIONAL CHANGE WHEN SINTERING AN IRON-BASED POWER MIXTURE



(57) Abstract: The invention concerns a method of controlling the dimensional change to a predetermined value including the steps of providing a first powder (A) consisting of an iron based powder(1) and copper in the form of elemental copper (2), or copper diffusion-bonded to said iron-based powder (3) ; providing a second powder (B) consisting of said iron-based powder (1) and a pre-alloyed iron-copper powder (4); mixing said first and second powder mixtures (A) and (B) in proportions resulting in the desired dimensional change adding graphite and lubricant and optionally hard phase materials and other alloying elements to the obtained mixture; compacting the obtained mixture; and sintering the compacted body.



MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

— of inventorship (Rule 4.17(iv)) for US only

**Published:**

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

## **A METHOD OF CONTROLLING THE DIMENSIONAL CHANGE WHEN SINTERING AN IRON-BASED POWER MIXTURE.**

The present invention concerns mixtures of iron-based powders. Particularly the invention concerns a method of controlling the dimensional change during sintering of compacts, which are prepared from such mixtures.

Sintering of powder metallurgically prepared compacts based on iron or iron with alloying elements normally results in a dimensional change, i.e. the dimensions of the sintered product deviate from those of the compact. The dimensional change is an obvious problem as various degrees of machining will then be necessary in order to obtain the identical sintered parts required in mass production.

The variation in dimensional change during sintering is particularly pronounced when copper is included in the compact. Copper is widely used as an alloying element due to its hardening effect. In contrast to most other elements, copper causes swelling when it is included in the powder to be compacted. Dimensional variation or instability caused by swelling during sintering of Fe-Cu and Fe-Cu-C-powder compacts have been studied for the past few decades. Different mechanisms have been suggested in order to explain the swelling of the compact during the sintering. Thus, Bockstiegel, (Metallurgia, 1962,3 (4), 67) proposed that the volume increase in Fe- Cu compacts during sintering was caused by solid state diffusion of Cu into the grains, leaving large pores at the original copper sites. Dautzenberg (Arch. Eisenhüttenwes., 1970, 41, 1005) conducted dilatometric studies and kinetic calculations and explained, on the basis of these studies, that diffusion alone could not be responsible for the rapid volumetric growth during sintering. The rapid expansion observed in the compacts was explained to be the effect of penetration of molten copper into the particle boundaries and along some of the grain boundaries inside the iron particles . The swelling effect of copper in different iron powders has been studied by several researches as for example Tabeshfar and Chadwick, (Powder Metall., 1984, 27, 19-24), who showed that the internal porosity left in iron particles after compaction effected the degree of swelling.

Within the patent literature the dimensional change has been addressed to in e.g. the US patent 5,567,890 which discloses an iron based powder including Ni, Mo and C for producing highly resistant components with small local variation in dimensional change. The dimen-

sional change of components produced by this powder composition is fairly independent of the sintered density and the carbon or molybdenum content. In these iron-based compositions copper can only be present as an impurity. The US patent 5,507,853 suggests a method of improving the dimensional stability of the iron- copper- carbon system by controlling the diffusion of graphite into the iron particle by adding selected oxides.

The Japanese patent application 53-146 204 describes an iron- copper- carbon sintered alloy, with good mechanical characteristics and dimensional accuracy. The copper swelling is suppressed by adding the copper as a prealloyed iron- copper powder.

In commercial powder metallurgical production dimensional change in sintered iron- copper- carbon parts is generally controlled by adding graphite to a combined carbon content of about 0.5 to about 0.8 %. Addition of graphite to a iron-copper system has a diminishing effect on the copper swelling and typically the growth can be kept below 0.4 %. By changing the particle size of added graphite the dimensional change can further be controlled within certain limits.

There is however a need of controlling the dimensional change within a wide limit without changing the chemical composition of the sintered compact and without adding large amounts of graphite or manipulating with the particle size of graphite. This is especially important when the same tool is used for plain iron- copper- carbon system as for high strength material, such as iron- molybdenum- copper- carbon, which is difficult to machine to right dimensions after sintering.

An object of the present invention is to provide a method of controlling the dimensional change during sintering for systems including copper and optionally also carbon and molybdenum. By the method according to the invention the dimensional change during sintering may be controlled to a predetermined value without changing the chemical composition. The possibility of predicting the dimensional change will reduce the need for machining and accordingly the cost of the final parts.

According to the invention the method of controlling the dimensional change to a predetermined value includes the steps of

- providing a first powder (A) consisting of
- an iron based powder(1) and copper in the form of elemental copper (2), or

- copper diffusion-bonded to said iron-based powder (3) ;
- providing a second powder (B) consisting of said iron-based powder (1) and a pre-alloyed iron-copper powder (4);
- mixing said first and second powder mixtures (A) and (B) in proportions resulting in the desired dimensional change;
- adding graphite and lubricant and optionally hard phase materials and other alloying elements to the obtained mixture;
- compacting the obtained mixture; and
- sintering the compacted body.

The actual proportion can easily be determined by the man skilled in the art by small scale laboratory experiments or by using full scale production equipment.

According to a preferred embodiment of the invention the iron-based powder (1) is an iron powder which is pre-alloyed with molybdenum.

In order to keep the same chemical composition for the mixtures and the sintered components produced from the mixtures with different proportions of the first powder A and the second powder B, the copper content of the first powder shall be the same as the copper content of the second powder. This can be achieved either by adjusting the Cu content of the powder A or adjusting the copper content of powder B. The copper content of powder B can be adjusted either by adjusting the proportions between powder (1) and powder (4) or adjusting the copper content of powder (4).

In order to obtain compacts having satisfactory mechanical properties according to the present invention it may be necessary to add minor amounts of graphite to the powder mixture to be compacted. Thus graphite in amounts between 0.1 – 1, preferably 0.2 – 1.0 and most preferably 0.2-0.8 % by weight of the total mixture to be compacted could be added before the compaction.

The powder mixture is also preferably combined with a lubricant before it is transferred to the die. Examples of suitable lubricants are e.g. stearates, waxes, oligomers, polymers etc. The lubricants are preferably added in the form of particles but may also be bonded to the particles. According to the present invention the amount of lubricant added to the iron-based

powder may vary between 0.05 and 1.5 %, preferably between 0.1- 1.0 % by weight of the mixture.

The compaction may be performed with standard equipment, at ambient or elevated temperature and the sintering may be performed at the temperatures normally used within the PM field, e.g. at low temperature such as 1100-1140°C or higher temperatures such as 1250°C and in conventionally used atmospheres.

An additional advantage by using the method of controlling the dimensional change according to the present invention is that annular composites consisting of one outer and one inner annular compact having the same chemical composition but different dimensional change may be produced. This makes it possible to achieve a firm bonding between the inner compact and the outer compact.

#### Example

Astaloy Mo, (available from Höganäs AB, Sweden) is a water atomised iron based powder pre-alloyed with 1.5 % of molybdenum. Astaloy Mo having 2 % by weight of copper diffusion bonded is also available from Höganäs AB as Distaloy DH-1. Distaloy DH-1 is in the following referred to as powder A.

Astaloy Mo mixed with 10 % of Astaloy 20Cu, which is a water atomised iron powder pre-alloyed with 20 % of copper and which is also available from Höganäs AB) was used as powder B.

Ten mixes were prepared with different proportions of powder A and powder B and different graphite contents. 0.6 % of Kenolube™ lubricant was added to all the mixes. The following mixes were made:

Mix no	Proportion of powder A %	proportion of powder B %	graphite %
1	100	0	0,4
3	70	30	0,4
5	50	50	0,4
7	30	70	0,4
9	0	100	0,4
2	100	0	0,6
4	70	30	0,6
6	50	50	0,6
8	30	70	0,6
10	0	100	0,6

After mixing and addition of lubricant fourteen tensile test samples for each mix were moulded, with a mould pressure of 600 MPa in a uniaxial press movement.

Seven of the produced tensile test samples of each mix were then sintered at 1120 °C, for 30 minutes, in an atmosphere of 90 %N<sub>2</sub>/10 %H<sub>2</sub> with a carbon potential of 0.2 % and the rest of the tensile test samples were sintered in endogas atmosphere, at 1120 °C, for 30 minutes, with a carbon potential of 0,5 %.

Dimensional change and mechanical properties of the samples were measured and the mean values based on seven samples treated during the same process conditions, were calculated.

Figure 1 shows the value of dimensional change from samples produced from mixes with different proportions between powder A and powder B. The figure shows that a very accurate predetermined value, in the range from +0.2 % to -0.14 %, of the dimensional change can be reached by changing the proportions of powder A and powder B.

Figure 2 shows the mean value of the sintered density, figure 3 shows the mean value of the ultimate tensile strength, figure 4 shows the mean value of elongation and figure 5 shows the mean value of the hardness for seven samples produced from the same mix and sintered under the same conditions. The figures show that the variations in sintered density, tensile strength, elongation and hardness are very small and within tolerable limits.

## CLAIMS

1. A method of controlling the dimensional change to a predetermined value when sintering a compacted body of a powder mixture characterised by providing a first powder (A) consisting of an iron based powder(1) and copper in the form of elemental copper (2), or copper diffusion-bonded to said iron-based powder (3) ; providing a second powder (B) consisting of said iron-based powder (1) and a pre-alloyed iron-copper powder (4); wherein the copper content of powder B is made equal to the copper content of powder A either by adjusting the Cu content of the powder A or adjusting the copper content of powder B, whereby the copper content of powder B is adjusted either by adjusting the proportions between powder (1) and powder (4) or by adjusting the copper content of powder (4).  
mixing said first and second powder mixtures (A) and (B) in proportions resulting in the desired dimensional change, adding graphite and lubricant and optionally hard phase materials and other alloying elements to the obtained mixture;  
compacting the obtained mixture to a compacted body; and  
sintering the compacted body.
2. The method according to claim 1 wherein the iron based powder (1) is an iron- molybdenum pre-alloyed powder.
3. A sintered powder metal compact produced according to the method of claim 1.



1/3




Figure 1




Figure 2




Figure 3




Figure 4




Figure 5

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 2003/001595

## A. CLASSIFICATION OF SUBJECT MATTER

IPC7: C22C 33/02

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC7: C22C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI, EPO-INTERNAL

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 02059388 A1 (FEDERAL-MOGUL SINTERED PRODUCTS LTD), 1 August 2002 (01.08.2002), page 6, line 5 - line 25, claims 14,20,21	3
A	--	1,2
X	WO 9110753 A1 (MANNESMANN AG), 25 July 1991 (25.07.1991)	3
A	--	1,2
X	GB 680275 A (HÖGANÄS-BILLESOLMS AKTIEBOLAG), 1 October 1952 (01.10.1952)	3
A	--	1,2

☒ Further documents are listed in the continuation of Box C.☒ See patent family annex.

\* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&amp;" document member of the same patent family

Date of the actual completion of the international search

21 January 2004

Date of mailing of the international search report

25 -01- 2004

Name and mailing address of the ISA/  
Swedish Patent Office  
Box 5055, S-102 42 STOCKHOLM  
Facsimile No. +46 8 666 02 86

Authorized officer

Nils Engnell/BS  
Telephone No. +46 8 782 25 00

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 2003/001595

## C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 6068813 A (FREDERICK J. SEMEL), 30 May 2000 (30.05.2000), column 3, line 26 - column 4, line 29; column 8, line 50 - column 9, line 21, Table 3,9	3
A	--	1,2
X	US 3752712 A (ROBERT T. HOLCOMB), 14 August 1973 (14.08.1973)	3
A	-- -----	1,2

## INTERNATIONAL SEARCH REPORT

Information on patent family members

24/12/2003

International application No.

PCT/SE 2003/001595

WO	02059388	A1	01/08/2002	AU	4860901	A	07/11/2001
				EP	1370704	A	17/12/2003
				GB	0101770	D	00/00/0000
				GB	0315414	D	00/00/0000
				GB	2386908	A	01/10/2003
				GB	0120401	D	00/00/0000

WO	9110753	A1	25/07/1991	AT	124467	T	15/07/1995
				CA	2074193	A,C	20/07/1991
				DE	4001900	A	25/07/1991
				DE	59009358	D	00/00/0000
				EP	0597832	A,B	25/05/1994
				SE	0597832	T3	
				JP	2908018	B	21/06/1999
				JP	5503318	T	03/06/1993

GB	680275	A	01/10/1952	NONE
----	--------	---	------------	------

US	6068813	A	30/05/2000	AU	765581	B	25/09/2003
				AU	3511300	A	18/12/2000
				CA	2369927	A	07/12/2000
				EP	1198317	A	24/04/2002
				JP	2003500538	T	07/01/2003
				TW	434063	B	00/00/0000
				WO	0073001	A	07/12/2000

US	3752712	A	14/08/1973	NONE
----	---------	---	------------	------